



0856/0866 Series LIFETIME Siliconized Acrylic Adhesive Sealant:

- **What is the base chemistry for the Lifetime Sealants?** A complex blend of proprietary acrylic emulsions, including terpolymers & styrenated acrylics, fortified with silicone & other proprietary additives.
- **What performance specifications do the Lifetime Sealants meet or exceed?** The Clear formula exceeds the requirements of ASTM C834-00 Type C. The White, Almond, Cedar/Woodtone, Brown, Gray & Black exceed the requirements of ASTM C920 Class 12 ½ (Fed Spec TT-S-00230C Class B) & ASTM C834-00 Type P.
- **Are the Lifetime Sealants paintable?** Yes, with latex or oil based paint.
- **Are the Lifetime Sealants water clean up?** Yes, before cure.
- **Are Lifetime Brand Sealants mildew-resistant?** Yes, the cured caulk is mildew-resistant. Although formula contains a fungicide for mildew-resistance, good housekeeping practices will also contribute to prevention.
- **Are Lifetime Brand Sealants suitable for below-grade applications?** No
- **What is the recommended Application Range for the Lifetime Sealants?** For best results, the Lifetime Brand Sealants should be applied between 40F & 90F, to clean, dry, sound substrates.
- **How long does it typically take for the Lifetime Clear Sealant to clear (applies white, dries clear)?** Depending upon factors such as bead size, substrate onto which the caulk is applied, temperature & humidity, a typical 3/16" bead of sealant will generally cure to a clear bead within 14 days. (In rare cases of high humidity combined with cool temperatures, clear time may be extended.)
- **Are there substrates on which the Lifetime Clear formula is not recommended?** Yes, sealant discoloration can occur when applied to copper, brass or zinc alloy-containing metals.
- **Where can I find additional information regarding these products?** Consult MSDS or TDS on this website (www.reddevil.com).