



0534PM Series Paint Master Vinyl Spackling Compound:

- **What is the base chemistry of Paint Master Vinyl Spackling Compound?** Vinyl Acrylic Emulsion Blend.
- **Is the 0534PM Series VOC Compliant?** Yes. Product suitable for sale in California & OTC areas.
- **Are any Prop 65 Ingredients used in the formulation of this product?** No.
- **Is Paint Master Vinyl Spackling suitable for water clean up?** Yes.
- **Does Paint Master Vinyl Spackling sand easily?** Yes. Following drying, product sands well. See MSDS for additional information, such as use of an appropriate respirator when sanding.
- **What color is the 0534PM Series as supplied?** White/slightly off-white.
- **What was Paint Master Vinyl Spackling designed to do primarily?** Provide excellent adhesion to plaster, drywall, wallboard, wood & primed metal. Works well for filling cracks in interior walls.
- **Are there surface preparation guidelines for Paint Master Vinyl Spackling?** Yes. Surface should be clean, dry & free from dust, dirt, grease, oil, mildew, wax, loose paint & old caulking. Apply only when spackling compound, air & surface temperatures are 50F to 90F. New or unpainted porous surfaces should be primed & allowed to dry before patching.
- **What is the consistency of Paint Master Vinyl Spackling as supplied?** Viscous smooth paste.
- **Is there an odor during application & drying?** Yes. A very low/mild latex odor is present during application & drying. Product is odor-free when cured.
- **Is 0534PM considered flammable?** No.
- **Is 0534PM Freeze-Thaw stable?** Yes. Product will withstand 5 F/T Cycles @ 0 degrees F & 72 degrees F, however for best results it is recommended that product be stored @ 40F to 90F.
- **How long does it typically take for 0534PM to become tack free?** Approximately 1 hr @ 77F. Conditions of cooler temperatures & higher humidity will extend drying time.
- **Is 0534PM suitable for painting with latex or oil based paint?** Yes. Allow approximately 2 hrs drying time for best results. Cool temperatures & higher humidity will extend drying time.
- **Should sanded patches always be primed & painted?** For best results, yes.
- **Is 0534PM suitable for interior or exterior applications?** No. Product designed for interior applications only.
- **Will this product exhibit any shrinkage during drying?** Yes. Vinyl Spackling may exhibit shrinkage after the initial application, requiring a

second application. Each applied patch should be allowed to completely dry, before application of subsequent material (approximately 1 to 2 hrs between applications, depending upon temperature, humidity & size of patch).

- **What is the standard packaging for Paint Master Vinyl Spackling?** HDPE Tub.
- **Where can additional information be found regarding 0534PM?** See MSDS & TDS on this website (www.reddevil.com).