

**0782 Paint Master 25 Year Painter's Acrylic Latex Caulk:**

- **What is the base chemistry of this product?** Proprietary acrylic emulsion.
- **Is 0782 VOC Compliant?** Yes. Product suitable for sale in California, OTC & other regulated areas.
- **Are any Prop 65 Ingredients added to this formulation?** Yes (see MSDS)
- **Is 0782 suitable for water clean up?** Yes.
- **Is 0782 paintable with either latex or oil based paints?** Yes. Allow 4 to 6 hrs drying time before painting. Larger beads & climatic conditions may extend (cooler temperatures & higher humidity will prolong drying time),
- **Is 0782 a mildew resistant product?** Yes. Cured bead is mildew resistant.
- **Does 0782 remain flexible after cure?** Yes.
- **How is the initial appearance of 0782 achieved?** Product manufactured under a unique Vacuumized process.
- **Does 0782 maintain flexibility after cure?** Yes.
- **Is 0782 a spec-compliant formulation?** Yes. Formula complies with ASTM C 834-05.
- **What basically was 0782 designed to do?** Provide Interior or Exterior seals on Windows, Doors, Trim, Vents, Railings, Countertops, Baseboards, Thresholds, Cracks & Joints.
- **Any guidelines for surface prep that should be followed?** Yes – consult cartridge label & TDS ([www.reddevil.com](http://www.reddevil.com)).
- **What color is 0782 as supplied?** White.
- **Does 0782 contain an adhesion promoter?** Yes.
- **Is 0782 considered flammable?** No.
- **What are the recommended storage conditions for this product?** 40F to 90F.
- **What is the recommended temperature range for product application?** 50F to 90F.
- **What packaging is 0782 available in?** Injection Molded HDPE Cartridge, 10.1 oz.
- **Is 0782 recommended for filling butt joints, correcting surface defects or tuck pointing?** No.
- **Other application limitations?** Not recommended for marine applications, on automobiles, aquariums or for applications below-grade or below waterline.
- **Is 0782 appropriate for joints subject to abrasion or wear?** Not recommended.
- **Can 0782 be thinned for certain applications?** Attempting to thin caulk not recommended.
- **How can maximum adhesion be achieved?** Prime bare surfaces before caulking.
- **Application limitations related to climate?** Yes, caulk should not be applied when rain or freezing temperatures are expected prior to cure.
- **How long should 0782 be protected from rain & or water?** 72 hrs.
- **What climatic conditions can slow drying time/cure?** Cooler temperatures &/or higher humidity.

- **Where can additional information be found on 0782 Paint Master Caulk?**  
See MSDS & TDS on this website ([www.reddevil.com](http://www.reddevil.com)).