

0792 Paint Master 55 Yr – Elastomeric Sealant:

- **What is the base chemistry of 0792 Elastomeric Sealant?** Proprietary acrylic emulsion polymer.
- **Is 0792 a VOC Compliant product?** Yes. Product is suitable for sale in California, OTC & similar areas.
- **Are any Prop 65 Ingredients added during the formulation of this sealant?** Yes. (See MSDS)
- **How is the initial appearance of 0792 achieved?** Product is manufactured under a unique vacuumized process.
- **Is 0792 paintable with either latex or oil based paint?** Yes. Allow 4 to 6 hrs drying time in normal climatic conditions (Cooler temperatures & higher humidity will extend drying time).
- **Does 0792 remain flexible after cure?** Yes.
- **Is 0792 suitable for water clean up before cure?** Yes.
- **Is 0792 a mildew resistant product?** Yes, cured bead is mildew resistant.
- **Is 0792 a spec-compliant product?** Yes. Product complies with ASTM C920 Class 25 & Federal Specification TT-S-00230C Class A.
- **What surface preparation guidelines are recommended for best results?** Surface must be clean, dry & free from dirt, dust, grease, oil, mildew, wax, loose paint & old caulking. Bare surfaces should be primed before caulking for best results. Apply only when sealant, air & substrate temperatures are 50F to 90F. Remove mildew from surface by scrubbing with a solution of 4 oz TSP (Trisodium Phosphate), 1 quart of liquid bleach mixed with 3 quarts of warm water. Protect eyes & skin by wearing goggles & chemical resistant gloves. Thoroughly rinse surface & allow to dry completely before caulking & painting.
- **What is the consistency of 0792 as supplied?** A smooth creamy paste.
- **What is the color of 0792 as supplied?** White as well as various core colors.
- **Is there any odor during application & cure?** Yes. A mild odor is present during application & cure. Product is odor-free @ full cure.
- **Is 0792 considered flammable?** No.
- **Is 0792 freeze-thaw stable?** Yes. Product will withstand 5 F/T Cycles @ 0 degrees F & 72 degrees F, however for best results product should be stored @ 40F to 90F.
- **When does an applied bead of 0792 typically become tack free?** 1 hour or less in normal climatic conditions. Conditions of cooler temperatures & higher humidity will prolong drying time.
- **What is the recommended temperature range for product application?** 50F to 90F.
- **Is 0792 suitable for automobiles, marine or below-grade applications?** Not recommended.
- **Is 0792 suitable for use on aquariums?** Not recommended.
- **Is 0792 suitable for below waterline applications?** No.
- **Is 0792 suitable for butt joints, smoothing surfaces or tuck pointing?** No.

- **Is 0792 suitable for use on new concrete?** No, new concrete should be allowed to cure a minimum of 30 days prior to any sealant application.
- **Is 0792 considered abrasion resistant after cure?** Product not recommended for applications where abrasion & wear are expected.
- **Can 0792 be thinned?** Not recommended.
- **How can adhesion to bare substrates be maximized?** Bare surfaces should be primed prior to caulking for best results.
- **How can a straight & neat bead edge be achieved?** Use masking tape on both sides of joint. Remove masking tape immediately after tooling bead & prior to formation of initial skin.
- **In what climatic conditions should 0792 not be applied?** Do not apply sealant when rain or freezing temperatures are expected. Apply only when caulk, air & substrate are 50F to 90F.
- **How long should 0792 be protected from rain or exposure to water?** 72 hrs. Conditions of cooler temperatures & higher humidity will slow down curing.
- **Is 0792 regulated by DOT?** No.
- **Where can additional information be found on 0792 Paint Master Acrylic Sealant?** See MSDS & TDS on this website (www.reddevil.com).