



0906/OI RD Pro 40 Year Caulk:

- **What is the base chemistry of 0906/OI?** Complex acrylic terpolymer blend.
- **Is 0906/OI VOC Compliant?** Yes. Product suitable for sale in California & OTC areas.
- **Are any Prop 65 Ingredients added during the formulation of this product?** No.
- **Is 0906/OI suitable for water clean up?** Yes.
- **Is 0906/OI paintable with latex or oil based paints?** Yes. Allow 4 to 6 hrs drying time before painting. Larger beads, cooler temperatures & higher humidity will extend drying time.
- **Is 0906/OI mildew resistant?** Yes. Cured bead is mildew resistant.
- **Does 0906/OI remain flexible after cure?** Yes.
- **How is the initial appearance of 0906/OI achieved?** Product manufactured under a unique Vacuumized process.
- **Is 0906/OI a spec-compliant formulation?** Yes. Formula complies with ASTM C834-00.
- **Any guidelines for surface preparation that should be followed?** Yes. Surface must be clean, dry & free from dirt, dust, grease, oil, mildew, wax, loose paint & old caulking. Bare surfaces should be primed before caulking for best results & application should take place when caulk, air & substrate are 50F to 90F. Mildew can be removed from surface by scrubbing with a solution of 4 oz TSP (Trisodium Phosphate), 1 quart of liquid bleach mixed with 3 quarts of warm water. Protect eyes & skin by wearing goggles & chemical resistant gloves. Thoroughly rinse surface & allow to dry completely before caulking & painting.
- **What color is 0906/OI as supplied?** White.
- **Does 0906/OI contain an adhesion promoter?** Yes.
- **How long should 0906/OI be protected from rain or water after application?** 72 hrs. Cooler temperatures & higher humidity can extend cure time.
- **What is the consistency of 0906/OI as supplied?** Smooth creamy paste.
- **Does 0906/OI have an odor during application & drying?** Yes. A mild/low odor is present that disappears with full cure.
- **Is 0906/OI considered flammable?** No.
- **Is 0906/OI considered Freeze-Thaw stable?** Yes. Product will withstand 5 F/T Cycles @ 0 degrees F & 72 degrees F, although for best results it is recommended that product be stored between 40F & 90F.
- **When does 0906/OI typically become tack free?** Approximately 1 hr or less in normal climatic conditions. Cooler temperatures & higher humidity will extend drying time.
- **What are the recommended conditions for product storage?** 40F to 90F.
- **What is the recommended temperature range for product application?** 50F to 90F.

- **What is the standard packaging for 0906/OI?** 10.1.oz HDPE Injection Molded Cartridge.
- **Is 0906/OI suitable for butt joints, correcting surface defects or tuck pointing?** Not recommended.
- **Other application limitations?** Not recommended for marine applications, on automobiles, aquariums or for applications below-grade or below waterline.
- **Is 0906/OI appropriate for joints subject to abrasion or wear?** Not recommended for joints subject to abrasion & wear.
- **Can 0906/OI be thinned?** Not recommended.
- **How can adhesion to bare surfaces be maximized?** Bare surfaces should be primed before caulking for best results.
- **Application limits related to climate?** Caulk should not be applied when rain or freezing temperatures are expected.
- **What climatic conditions will slow down drying-time?** Cooler temperatures &/or higher humidity.
- **Where can additional information be found on 0906/OI?** See MSDS & TDS on this website (www.reddevil.com).