



# Red Devil

## Blacktop & Roof

Blacktop & Roof Repair Sealant provides a durable, flexible and weather-resistant seal for cracks and joints in asphalt driveways, parking lots and more. It is also ideal for waterproofing, repairing and sealing roofs, shingles and flashings around chimneys and skylights. It provides excellent adhesion and prevents water and frost damage.

### FEATURES:


- Forms an Extra Tight Seal
- Adheres in Damp Surfaces
- Water Resistant
- Permanently Flexible
- Solvent Clean Up
- Textured Appearance
- Suitable for Below Grade Applications
- Spec-Compliant

### USES:

Formulated for use on Driveways, Parking Lots, Skylights, Shingles, Chimney Flashings & More.

### ADHERES TO:

Asphalt, Blacktop, Wood, Concrete, Brick, Cinder Block, Metal & More.



SUITABLE FOR  
BELOW GRADE  
AREAS



PERMANENT  
FLEXIBILITY



FORMS A WATER-  
RESISTANT SEAL



WATER  
CLEAN-UP



MADE  
IN THE USA



[www.reddevil.com](http://www.reddevil.com)

Customer Service: 1-800-423-3845

Red Devil, Inc.  
4175 Webb Street  
Pryor, OK 74361

# TECHNICAL DATA SHEET

## BLACKTOP & ROOF REPAIR SEALANT

PART#	COLOR	PACKAGE	UPC #	CASE QTY.
0636	Black	10.1 fl. oz (300 mL) Cartridge	0-75339-00636-8	12

### PHYSICAL & CHEMICAL PROPERTIES:

Weight Per Gallon: 9.60 +/- 0.50

Specific Gravity: Approx. 1.25

Total Non-Volatile % Solids (Weight): Approx. 83% +/-3

Consistency/Appearance: Heavy Bodied Textured Paste

Base Polymer: Petroleum Asphalt Blend

Odor: Solvent

Pigment/Filler: Calcium Carbonate

Flash Point: 100°F (38°C)

Freeze/Thaw Stability: Passes 5 Cycles

Shelf Life: Expect 1 year @ 72°F

Tack Free Time: 4 Hours

Water Resistance: Excellent @ Full Cure

Storage Conditions: Original Container: 40°F to 90°F

Application emperature: 40°F to 90°F

Service Temperature: -25°F to 220°F

Tooling/Workability: Excellent

Extrusion Viscosity: 120 seconnds +/-30

Shrinkage: < 40%

Coverages: 30 Linear Feet

Accelerated Weathering: No Cracking @ 5,000 Hours QUV

Low Temperature Flexibility: Passed

Slump: <0.50 @ 122°F (40°C)

### APPLICATION:

Remove old caulking/sealant. Clean, dry & remove any loose material, from the surface, that may interfere with adhesion, including dirt, debris, oil, and residue. Cut the nozzle tip to the desired bead size at a 45° angle. Load the cartridge into a standard-sized caulking gun and apply sealant to the gap or joint. Smooth sealant using a damp cloth or finishing tool for a professional finish. Remove excess sealant with a damp cloth before it skins over. Allow the sealant to dry before painting.

### FOR BEST RESULTS:

- Store sealant away from extreme heat or cold conditions
- Best application temperature range, 40°F to 90°F. joint size should not exceed 1/2". If joint depth exceeds 1/4", use a backer rod.
- Do not use for filling butt joints, correcting surface defects or for tuck pointing.
- Prime bare surfaces before caulking

### LIMITATIONS:

- Not recommended for use on automotives, fish tanks/aquariums.
- Not recommended for below waterline or below-grade applications.
- Should not be exposed to rain or freezing temperatures within 72 hours of application - Cooler temperatures & higher humidity will extend the cure time.

### CLEAN-UP:

Clean tools immediately with mineral spirits. Dried sealant must be scraped away. Wash skin with warm water and soap.

### LIMITED WARRANTY:

Recommendations for use of this product are based on tests we believe to be reliable. Manufacturer and seller are not responsible for results where this product is used under conditions beyond our control. If when applied as directed, this material peels, cracks or separates, it will be replaced without charge upon presentation of proof of purchase and used cartridge. This limited warranty only applies to residential use and damages including consequential damage and other remedies are excluded. No other warranties apply, including fitness for a particular purpose.

**CAUTION: NOT FOR INTERNAL CONSUMPTION. KEEP OUT OF REACH OF CHILDREN & PETS. KEEP FROM FREEZING. (See SDS for additional safety information)**

**⚠ WARNING: Reproductive Harm Risk from Ethylene Glycol & Cancer Risk From Titanium Dioxide Exposure - [www.P65Warnings.ca.gov](http://www.P65Warnings.ca.gov)**

CRITERIA	STATUS
CARB Compliance	Yes
Prop 65 Ingredients	Yes (See SDS)
DOT Proper Shipping Name	Not Regulated by DOT
DOT Hazzard	None
DOT UN/NA Number	None
Packing Group	None
VOC Content	< 20 % by weight, < 200 g/L