

# STRONG BOND

Strong Bond™ Heavy-Duty Adhesive & Sealant is specially formulated with premium performance in mind. This advanced hybrid polymer technology holds heavy applications quickly and achieves a strong, permanent bond to both porous and non-porous substrates. This all-in-one adhesive and sealant provides more than double the initial bond strength of most other adhesives. Use Strong Bond™ for fast instant strength, eliminating the need for nails, screws, or fasteners in most applications.

#### **FEATURES:**

- Immediate Powerful Green Strength
- No Solvents or Water, Will Not Shrink
- All-Weather, Multi-Surface Application
- Remains Flexible, Allows for Vibration/Movement
- Mold & Mildew Resistant When Cured
- Interior/Exterior
- VOC Compliant, 100% Solids

#### **USES:**

Engineered with excellent green strength and fixturing properties. It not only bonds well to a variety of substrates but it also grabs and holds, which helps reduce assembly time, brace usages, fastener usage and more.

#### **ADHERES TO:**

Wood, Plaster, Brick, Concrete, Stone, Masonry, Aluminum, Most Metals, Vinyl, Glass, Tile, Ceramics, Marble, Fiberglass, EIFS, Stucco, PVC/Plastics, EPS or Styrofoam Insulation, EPDM & More.







**FLEXIBILITY** 



**ALL-WEATHER** APPLICATION



**MOLD & MILDEW** RESISTANT WHEN CURED





· WHITE . BLANCO .

- ASTM C920, Class 25
- USDA Compliant















## **TECHNICAL DATA SHEET**

## **Strong Bond**<sup>™</sup>

PART#	COLOR	PACKAGE	UPC #	CASE QTY.	
0956	White	9.0 fl. oz (266 mL) Cartridge	0-75339-00956-7	12	

#### PHYSICAL & CHEMICAL PROPERTIES:

**Viscosity:** 1,800,000 cps (Spindle 7, 4rpm) **Skin Formation:** 10 Minutes (70°F, 50% RH)

**Density:** 14.8 lbs./gal (ASTM D1475)

**Consistency/Appearance:** Smooth, Viscous Paste

**Odor:** Odorless

**Base Polymer: Proprietary MS Polymer Blend** 

Slump/Sag: 0 (Pass)

Hardness: 45 (Shore A) (ASTM C661) Shelf Life: Minimum 1 Year @ 72°F Modulus 100%: 1.42 MPa (ASTM D412) Tensile Strength: 1.58 MPa (ASTM D412)

Storage Conditions: Below 77°F (25°C) Cool & Dry Place

Elongation at Break: 150% (ASTM D412) Lap Shear: 2.15 MPa (ASTM D412)

Cure in Depth After 7 Days: 13mm (70°F, 50% RH) Service Temperature: -50°F to 220°F (-46°C to 104°C)

**QUV Testing:** Pass (2,000 Hours) (ASTM G26)

CRITERIA	STATUS	
CARB Compliance	Yes	
Prop 65 Ingredients	None	
DOT Proper Shipping Name	Not Regulated by DOT	
DOT Hazzard	None	
DOT UN/NA Number	None	
Packing Group	None	
VOC Content	< 9.55 g/L	

#### APPLICATION:

Remove old caulking/sealant. Surface must be clean, dry & free from dirt, dust, grease, oil, mildew, wax, loose paint, frost, & other residue or material that may interfere with adhesion. Clip off tip of nozzle/spout @ 45° angle to desired bead size. Load cartridge into caulking gun. Fill deep voids to within ½" of surface with solid filler. Smooth caulk using a Caulk Smoother or Putty Knife. Wait until product is tack free before painting. Use mineral spirits to clean uncured sealant from surfaces and tools. Use soap and water to clean uncured sealant from hands and skin.

#### **FOR BEST RESULTS:**

- Prime porous surfaces before caulking.
- Use with adequate ventilation.
- Store product below 77°F (25°C) Away from extreme heat or moisture.

#### **LIMITATIONS:**

- Do not store at elevated temperatures.
- Use on clean surfaces free of contaminations.
- Cold temperatures and low humidity will slow curing.
- Protect from freezing.
- Do not use on olefins such as polyethylene, polypropylene, or TPO prior to testing.
- Long-term sumersion under water can cuase loss of adhesion on some substrates.

### LIMITED WARRANTY:

Recommendations for use of this product are based on tests we believe to be reliable. Manufacturer and seller are not responsible for results where this product is used under conditions beyond our control. If when applied as directed, this material peels, cracks or separates, it will be replaced without charge upon presentation of proof of purchase and used cartridge. This limited warranty only applies to residential use and damages including consequential damage and other remedies are excluded. No other warranties apply, including fitness for a particular purpose.

CAUTION: NOT FOR INTERNAL CONSUMPTION. KEEP OUT OF REACH OF CHILDREN & PETS. KEEP FROM FREEZING. (See SDS for additional safety information)