



# Red Devil

## FLOORING REPAIR FILLER

Flooring Repair Filler is specially formulated to fill chips and seams commonly found in solid hardwood, engineered hardwood, laminate, LVP, LVT, and tile floors. It dries hard, blends with general flooring colors, and cleans up easily with water.

### FEATURES:

- Permanently Fills Chips & Seams
- Matches Various Wood Finishes
- Dries Quick
- Dries Hard
- Won't Shrink or Crack
- Superior Adhesion
- Easy Water Clean up
- Low Odor

### ADHERES TO:

- Natural Hardwood
- Plywood
- Natural Softwood
- Particle Board
- Composite Wood
- Fiberboard

### USE ON:

- Solid Wood Floors
- Engineered Hardwood Floors
- Laminate Floors
- Luxury Vinyl Floors
- Moldings & Trim



Meets or Exceeds Federal Specifications:

- ASTM D2240
- ASTM D638



MULTI-SURFACE  
APPLICATION



QUICK  
DRY TIME



WATER  
CLEAN UP



WON'T SHRINK  
OR CRACK



[www.reddevil.com](http://www.reddevil.com)

Customer Service: 1-800-423-3845

Red Devil, Inc.  
4175 Webb Street  
Pryor, OK 74361

# TECHNICAL DATA SHEET

## 100% SILICONE WATERPROOF FLOORING PERIMETER SEALANT

PART#	COLOR	PACKAGE	UPC #	CASE QTY.
056020	Light Wood	5 fl. oz (148 mL) Squeeze Tube	0-7533903974-8	4
056025	Medium Wood	5 fl. oz (148 mL) Squeeze Tube	0-7533903976-2	4
056045	Dark Wood	5 fl. oz (148 mL) Squeeze Tube	0-7533903978-6	4
056050	Medium Gray	5 fl. oz (148 mL) Squeeze Tube	0-7533903970-0	4
056055	Dark Gray	5 fl. oz (148 mL) Squeeze Tube	0-7533903972-4	4
056070	Dark Mahogany	5 fl. oz (148 mL) Squeeze Tube	0-7533903980-9	4

### PHYSICAL & CHEMICAL PROPERTIES:

**Weight Per Gallon:** 12.85

**Total Non-Volatile % Solids (Weight):** 77%

**Shore A Hardness:** 90

**Shore D Hardness:** 13

**Tensile Strength:** 451 psi

**Shear Strength:** 137 psi

**Elongation:** 21%

**Dry Time:** 10 Minutes

**Tack Free Time:** 15 Minutes

**Full Cure:** 24 Hours

**Extrudability/Application:** Approx. 190 Seconds

**Slump:** Approx. 0.025 in.

**Consistency/Appearance:** Stiff Paste

**Odor:** Low

**Shelf Life:** 12 Months @ 72°F

**Application Temperature:** 40°F to 100°F (4°C to 38°C)

**Clean-Up:** Water

**Coverage (3/16" bead):** Approx. 25 Linear Feet

### APPLICATION:

Clean and dry surface of application area. Knead the tube before cutting and extruding material. Clip off the nozzle tip at a 45° angle to desired bead size. Apply Repair Filler into area to be filled. Use a putty knife to smooth over and press into the chip or seam. Clean up any excess Repair Filler with a damp rag or sponge. Allow applied Repair Filler to full cure for 24 hours.

### LIMITATIONS:

- Apply at a surface and air temperature between 40°F - 90°F.
- Keep from freezing.
- If the cavity is greater than 1/2" deep, a second application is recommended after 24 hours.

### LIMITED WARRANTY:

Recommendations for use of this product are based on tests we believe to be reliable. Manufacturer and seller are not responsible for results where this product is used under conditions beyond our control. If when applied as directed, this material peels, cracks or separates, it will be replaced without charge upon presentation of proof of purchase and used cartridge. This limited warranty only applies to residential use and damages including consequential damage and other remedies are excluded. No other warranties apply, including fitness for a particular purpose.

CRITERIA	STATUS
CARB Compliance	Yes
Prop 65 Ingredients	Yes (See SDS)
DOT Proper Shipping Name	Not Regulated by DOT
DOT Hazzard	None
DOT UN/NA Number	None
Packing Group	None

**CAUTION: NOT FOR INTERNAL CONSUMPTION. KEEP OUT OF REACH OF CHILDREN & PETS. KEEP FROM FREEZING. (See SDS for additional safety information)**

**⚠ WARNING: Cancer Risk and Reproductive Harm - [www.P65Warnings.ca.gov](http://www.P65Warnings.ca.gov)**