## 0840, 0846, 0846/20, 0846/30, 0846/35, 0846/40, 0846/50, 0846/60, 0849/0876 Series Window & Door Siliconized Acrylic Caulks:

- What is the base chemistry for 35 Yr Window & Door Sealants? Siliconized Acrylic Emulsion Polymer.
- Are the 0846 Series White & Colors & 0876 Clear compliant to any performance specifications? Yes. White & Colors are compliant to ASTM C 834-05 Type P (pigmented formulations) & Clear is compliant to ASTM C 834-05 Type C (clear formulations).
- What colors is the **0846 Series available in?** White, Almond, Cedar, Dark Brown, Gray & Black.
- Are the 0846 Series Sealants & 0876 water clean up? Yes.
- Are the caulks suitable for interior or exterior applications? Yes.
- Are the sealants paintable? Yes. White is paintable following 2 to 6 hrs; longer drying time may be required in conditions of cooler temperatures & higher humidity. The colors are also paintable, should a color change be desired @ a future point. Clear is paintable following full transition from white to clear (typically < 2 weeks)
- **Does 0876 Clear apply clear?** No; the acrylic clear applies white & turns clear within about 14 days, depending upon climatic conditions, bead size & porosity of substrate.
- Are the 0846/0876 Series 35 Year Sealants suitable for below-grade applications? No.
- What is the recommended application temperature range? 40F & rising, to 90F.
- Are the 0846/0876 Series 35 Year Sealants UL Listed? No.
- Are the 0846/0876 Series 35 Year Sealants mildew resistant? Yes.
- Are the 0846/0876 Series 35 Year Sealants VOC Compliant? Yes.
- Are any Prop 65 Listed raw materials added to the 0846/0876 35 Year Sealants? Yes (see MSDS)
- Where can additional information be found on this product? See MSDS & TDS on this website (www.reddevil.com).